

Building Materials and the Ancient Quarries at Thamugadi (East of Algeria), Case Study: Sandstone and Limestone

Rezkallah, Younès; Marmi, Ramdane

Source / Izvornik: **ASMOSIA XI, Interdisciplinary Studies on Ancient Stone, Proceedings of the XI International Conference of ASMOSIA, 2018, 673 - 682**

Conference paper / Rad u zborniku

Publication status / Verzija rada: **Published version / Objavljena verzija rada (izdavačev PDF)**

<https://doi.org/10.31534/XI.asmosia.2015/05.07>

Permanent link / Trajna poveznica: <https://urn.nsk.hr/urn:nbn:hr:123:894784>

Rights / Prava: [In copyright](#) / [Zaštićeno autorskim pravom.](#)

Download date / Datum preuzimanja: **2024-11-21**



Repository / Repozitorij:

[FCEAG Repository - Repository of the Faculty of Civil Engineering, Architecture and Geodesy, University of Split](#)





ASMOSIA XI

Interdisciplinary Studies on Ancient Stone

PROCEEDINGS

of the XI ASMOSIA Conference, Split 2015

Edited by Daniela Matetić Poljak and Katja Marasović



Interdisciplinary Studies on Ancient Stone
Proceedings of the XI ASMOSIA Conference (Split 2015)

Publishers:

ARTS ACADEMY IN SPLIT
UNIVERSITY OF SPLIT

and

UNIVERSITY OF SPLIT
FACULTY OF CIVIL ENGINEERING,
ARCHITECTURE AND GEODESY

Technical editor:
Kate Bošković

English language editor:
Graham McMaster

Computer pre-press:
Nikola Križanac

Cover design:
Mladen Čulić

Cover page:

Sigma shaped mensa of pavonazzetto marble from Diocletian's palace in Split

ISBN 978-953-6617-49-4 (Arts Academy in Split)

ISBN 978-953-6116-75-1 (Faculty of Civil Engineering, Architecture and Geodesy)

e-ISBN 978-953-6617-51-7 (Arts Academy in Split)

e-ISBN 978-953-6116-79-9 (Faculty of Civil Engineering, Architecture and Geodesy)

CIP available at the digital catalogue of the University Library in Split, no 170529005

Association for the Study of Marble & Other Stones in Antiquity

ASMOSIA XI

Interdisciplinary Studies of Ancient Stone

Proceedings of the Eleventh International Conference of ASMOSIA,
Split, 18–22 May 2015

Edited by
Daniela Matetić Poljak
Katja Marasović



Split, 2018

Nota bene

All papers are subjected to an international review.

The quality of the images relies on the quality of the originals provided by the authors.

CONTENT

PRESENTATION	15
NECROLOGY: NORMAN HERZ (1923-2013) by Susan Kane	17
1. APPLICATIONS TO SPECIFIC ARCHEOLOGICAL QUESTIONS – USE OF MARBLE	
Hermaphrodites and Sleeping or Reclining Maenads: Production Centres and Quarry Marks <i>Patrizio Pensabene</i>	25
First Remarks about the Pavement of the Newly Discovered Mithraeum of the Colored Marbles at Ostia and New Investigations on Roman and Late Roman White and Colored Marbles from Insula IV, IX <i>Massimiliano David, Stefano Succi and Marcello Turci</i>	33
Alabaster. Quarrying and Trade in the Roman World: Evidence from Pompeii and Herculaneum <i>Simon J. Barker and Simona Perna</i>	45
Recent Work on the Stone at the Villa Arianna and the Villa San Marco (Castellammare di Stabia) and Their Context within the Vesuvian Area <i>Simon J. Barker and J. Clayton Fant</i>	65
Marble Wall Decorations from the Imperial Mausoleum (4 th C.) and the Basilica of San Lorenzo (5 th C.) in Milan: an Update on Colored Marbles in Late Antique Milan <i>Elisabetta Neri, Roberto Bugini and Silvia Gazzoli</i>	79
Sarcophagus Lids Sawn from their Chests <i>Dorothy H. Abramitis and John J. Herrmann</i>	89
The Re-Use of Monolithic Columns in the Invention and Persistence of Roman Architecture <i>Peter D. De Staebler</i>	95
The Trade in Small-Size Statues in the Roman Mediterranean: a Case Study from Alexandria <i>Patrizio Pensabene and Eleonora Gasparini</i>	101
The Marble Dedication of Komon, Son of Asklepiades, from Egypt: Material, Provenance, and Reinforcement of Meaning <i>Patricia A. Butz</i>	109
Multiple Reuse of Imported Marble Pedestals at Caesarea Maritima in Israel <i>Barbara Burrell</i>	117
Iasos and Iasian Marble between the Late Antique and Early Byzantine Eras <i>Diego Peirano</i>	123

Thassos, Known Inscriptions with New Data <i>Tony Kozelj and Manuela Wurch-Kozelj</i>	131
The Value of Marble in Roman <i>Hispalis</i> : Contextual, Typological and Lithological Analysis of an Assemblage of Large Architectural Elements Recovered at N° 17 Goyeneta Street (Seville, Spain) <i>Ruth Taylor, Oliva Rodríguez, Esther Ontiveros, María Luisa Loza, José Beltrán and Araceli Rodríguez</i>	143
<i>Giallo Antico</i> in Context. Distribution, Use and Commercial Actors According to New Stratigraphic Data from the Western Mediterranean (2 nd C. Bc – Late 1 st C. Ad) <i>Stefan Ardeleanu</i>	155
<i>Amethystus</i> : Ancient Properties and Iconographic Selection <i>Luigi Pedroni</i>	167
2. PROVENANCE IDENTIFICATION I: (MARBLE)	
Unraveling the Carrara – Göktepe Entanglement <i>Walter Prochaska, Donato Attanasio and Matthias Bruno</i>	175
The Marble of Roman Imperial Portraits <i>Donato Attanasio, Matthias Bruno, Walter Prochaska and Ali Bahadır Yavuz</i>	185
Tracing Alabaster (Gypsum or Anhydrite) Artwork Using Trace Element Analysis and a Multi-Isotope Approach (Sr, S, O) <i>Lise Leroux, Wolfram Kloppmann, Philippe Bromblet, Catherine Guerrot, Anthony H. Cooper, Pierre-Yves Le Pogam, Dominique Vingtain and Noel Worley</i>	195
Roman Monolithic Fountains and Thasian Marble <i>Annewies van den Hoek, Donato Attanasio and John J. Herrmann</i>	207
Archaeometric Analysis of the Alabaster Thresholds of Villa A, Oplontis (Torre Annunziata, Italy) and New Sr and Pb Isotopic Data for <i>Alabastro Ghiaccione del Circeo</i> <i>Simon J. Barker, Simona Perna, J. Clayton Fant, Lorenzo Lazzarini and Igor M. Villa</i>	215
Roman Villas of Lake Garda and the Occurrence of Coloured Marbles in the Western Part of “Regio X Venetia et Histria” (Northern Italy) <i>Roberto Bugini, Luisa Folli and Elisabetta Roffia</i>	231
Calcitic Marble from Thasos in the North Adriatic Basin: Ravenna, Aquileia, and Milan <i>John J. Herrmann, Robert H. Tykot and Annewies van den Hoek</i>	239
Characterisation of White Marble Objects from the Temple of Apollo and the House of Augustus (Palatine Hill, Rome) <i>Francesca Giustini, Mauro Brilli, Enrico Gallochio and Patrizio Pensabene</i>	247
Study and Archeometric Analysis of the Marble Elements Found in the Roman Theater at Aeclanum (Mirabella Eclano, Avellino - Italy) <i>Antonio Mesisca, Lorenzo Lazzarini, Stefano Cancelliere and Monica Salvadori</i>	255

Two Imperial Monuments in Puteoli: Use of Proconnesian Marble in the Domitianic and Trajanic Periods in Campania <i>Irene Bald Romano, Hans Rupprecht Goette, Donato Attanasio and Walter Prochaska</i>	267
Coloured Marbles in the Neapolitan Pavements (16 th And 17 th Centuries): the Church of <i>Santi Severino e Sossio</i> <i>Roberto Bugini, Luisa Folli and Martino Solito</i>	275
Roman and Early Byzantine Sarcophagi of Calcitic Marble from Thasos in Italy: Ostia and Siracusa <i>Donato Attanasio, John J. Herrmann, Robert H. Tykot and Annewies van den Hoek</i>	281
Revisiting the Origin and Destination of the Late Antique Marzamemi 'Church Wreck' Cargo <i>Justin Leidwanger, Scott H. Pike and Andrew Donnelly</i>	291
The Marbles of the Sculptures of Felix Romuliana in Serbia <i>Walter Prochaska and Maja Živić</i>	301
Calcitic Marble from Thasos and Proconnesos in Nea Anchialos (Thessaly) and Thessaloniki (Macedonia) <i>Vincent Barbin, John J. Herrmann, Aristotle Mentzos and Annewies van den Hoek</i>	311
Architectural Decoration of the Imperial Agora's Porticoes at Iasos <i>Fulvia Bianchi, Donato Attanasio and Walter Prochaska</i>	321
The Winged Victory of Samothrace - New Data on the Different Marbles Used for the Monument from the Sanctuary of the Great Gods <i>Annie Blanc, Philippe Blanc and Ludovic Laugier</i>	331
Polychrome Marbles from the Theatre of the Sanctuary of Apollo Pythios in Gortyna (Crete) <i>Jacopo Bonetto, Nicolò Mareso and Michele Bueno</i>	337
Paul the Silentiary, Hagia Sophia, Onyx, Lydia, and Breccia Corallina <i>John J. Herrmann and Annewies van den Hoek</i>	345
Incrustations from Colonia Ulpia Traiana (Near Modern Xanten, Germany) <i>Vilma Ruppiniè and Ulrich Schüssler</i>	351
Stone Objects from Vindobona (Austria) – Petrological Characterization and Provenance of Local Stone in a Historico-Economical Setting <i>Andreas Rohatsch, Michaela Kronberger, Sophie Insulander, Martin Mosser and Barbara Hodits</i>	363
Marbles Discovered on the Site of the Forum of Vaison-la-Romaine (Vaucluse, France): Preliminary Results <i>Elsa Roux, Jean-Marc Mignon, Philippe Blanc and Annie Blanc</i>	373
Updated Characterisation of White Saint-Béat Marble. Discrimination Parameters from Classical Marbles <i>Hernando Royo Plumed, Pilar Lapeunte, José Antonio Cuchí, Mauro Brillì and Marie-Claire Savin</i>	379

Grey and Greyish Banded Marbles from the Estremoz Anticline in Lusitania <i>Pilar Lapuente, Trinidad Nogales-Basarrate, Hernando Royo Plumed, Mauro Brilli and Marie-Claire Savin</i>	391
New Data on Spanish Marbles: the Case of <i>Gallaecia</i> (NW Spain) <i>Anna Gutiérrez García-M., Hernando Royo Plumed and Silvia González Soutelo</i>	401
A New Roman Imperial Relief Said to Be from Southern Spain: Problems of Style, Iconography, and Marble Type in Determining Provenance <i>John Pollini, Pilar Lapuente, Trinidad Nogales-Basarrate and Jerry Podany</i>	413
Reuse of the <i>Marmorata</i> from the Late Roman Palatial Building at Carranque (Toledo, Spain) in the Visigothic Necropolis <i>Virginia García-Entero, Anna Gutiérrez García-M. and Sergio Vidal Álvarez</i>	427
Imperial Porphyry in Roman Britain <i>David F. Williams</i>	435
Recycling of Marble: Apollonia/Sozousa/Arsuf (Israel) as a Case Study <i>Moshe Fischer, Dimitris Tambakopoulos and Yannis Maniatis</i>	443
Thasian Connections Overseas: Sculpture in the Cyrene Museum (Libya) Made of Dolomitic Marble from Thasos <i>John J. Herrmann and Donato Attanasio</i>	457
Marble on Rome's Southwestern Frontier: Thamugadi and Lambaesis <i>Robert H. Tykot, Ouahiba Bouzidi, John J. Herrmann and Annewies van den Hoek</i>	467
Marble and Sculpture at Lepcis Magna (Tripolitania, Libya): a Preliminary Study Concerning Origin and Workshops <i>Luisa Musso, Laura Buccino, Matthias Bruno, Donato Attanasio and Walter Prochaska</i>	481
The Pentelic Marble in the Carnegie Museum of Art Hall of Sculpture, Pittsburgh, Pennsylvania <i>Albert D. Kollar</i>	491
Analysis of Classical Marble Sculptures in the Michael C. Carlos Museum, Emory University, Atlanta <i>Robert H. Tykot, John J. Herrmann, Renée Stein, Jasper Gaunt, Susan Blevins and Anne R. Skinner</i>	501
3. PROVENANCE IDENTIFICATION II: (OTHER STONES)	
Aphrodisias and the Regional Marble Trade. The <i>Scaenae Frons</i> of the Theatre at Nysa <i>Natalia Toma</i>	513
The Stones of Felix Romuliana (Gamzigrad, Serbia) <i>Bojan Djurić, Divna Jovanović, Stefan Pop Lazić and Walter Prochaska</i>	523
Aspects of Characterisation of Stone Monuments from Southern Pannonia <i>Branka Migotti</i>	537

The Budakalász Travertine Production <i>Bojan Djurić, Sándor Kele and Igor Rižnar</i>	545
Stone Monuments from Carnuntum and Surrounding Areas (Austria) – Petrological Characterization and Quarry Location in a Historical Context <i>Gabrielle Kremer, Isabella Kitz, Beatrix Moshhammer, Maria Heinrich and Erich Draganits</i>	557
Espejón Limestone and Conglomerate (Soria, Spain): Archaeometric Characterization, Quarrying and Use in Roman Times <i>Virginia García-Entero, Anna Gutiérrez García-M, Sergio Vidal Álvarez, María J. Peréx Agorreta and Eva Zarco Martínez</i>	567
The Use of Alcover Stone in Roman Times (<i>Tarraco, Hispania Citerior</i>). Contributions to the <i>Officina Lapidaria Tarraconensis</i> <i>Diana Gorostidi Pi, Jordi López Vilar and Anna Gutiérrez García-M.</i>	577
4. ADVANCES IN PROVENANCE TECHNIQUES, METHODOLOGIES AND DATABASES	
Grainautline – a Supervised Grain Boundary Extraction Tool Supported by Image Processing and Pattern Recognition <i>Kristóf Csorba, Lilla Barancsuk, Balázs Székely and Judit Zöldföldi</i>	587
A Database and GIS Project about Quarrying, Circulation and Use of Stone During the Roman Age in <i>Regio X - Venetia et Histria</i> . The Case Study of the Euganean Trachyte <i>Caterine Previato and Arturo Zara</i>	597
5. QUARRIES AND GEOLOGY	
The Distribution of Troad Granite Columns as Evidence for Reconstructing the Management of Their Production <i>Patrizio Pensabene, Javier Á. Domingo and Isabel Rodà</i>	613
Ancient Quarries and Stonemasonry in Northern Choria Considiana <i>Hale Güney</i>	621
Polychromy in Larisaeon Quarries and its Relation to Architectural Conception <i>Gizem Mater and Ertunç Denктаş</i>	633
Euromos of Caria: the Origin of an Hitherto Unknown Grey Veined Stepped Marble of Roman Antiquity <i>Matthias Bruno, Donato Attanasio, Walter Prochaska and Ali Bahadır Yavuz</i>	639
Unknown Painted Quarry Inscriptions from Bacakale at <i>Docimium</i> (Turkey) <i>Matthias Bruno</i>	651
The Green Schist Marble Stone of Jebel El Hairech (North West of Tunisia): a Multi-Analytical Approach and its Uses in Antiquity <i>Ameur Younès, Mohamed Gaied and Wissem Gallala</i>	659
Building Materials and the Ancient Quarries at <i>Thamugadi</i> (East of Algeria), Case Study: Sandstone and Limestone <i>Younès Rezkallah and Ramdane Marmi</i>	673

The Local Quarries of the Ancient Roman City of <i>Valeria</i> (Cuenca, Spain) <i>Javier Atienza Fuente</i>	683
The Stone and Ancient Quarries of Montjuïc Mountain (Barcelona, Spain) <i>Aureli Álvarez</i>	693
<i>Notae Lapidinarum</i> : Preliminary Considerations about the Quarry Marks from the Provincial Forum of <i>Tarraco</i> <i>Maria Serena Vinci</i>	699
The Different Steps of the Rough-Hewing on a Monumental Sculpture at the Greek Archaic Period: the Unfinished Kouros of Thasos <i>Danièle Braunstein</i>	711
A Review of Copying Techniques in Greco-Roman Sculpture <i>Séverine Moureaud</i>	717
Labour Forces at Imperial Quarries <i>Ben Russell</i>	733
Social Position of Craftsmen inside the Stone and Marble Processing Trades in the Light of Diocletian's Edict on Prices <i>Krešimir Bosnić and Branko Matulić</i>	741
6. STONE PROPERTIES, WEATHERING EFFECTS AND RESTORATION, AS RELATED TO DIAGNOSIS PROBLEMS, MATCHING OF STONE FRAGMENTS AND AUTHENTICITY	
Methods of Consolidation and Protection of Pentelic Marble <i>Maria Apostolopoulou, Elissavet Drakopoulou, Maria Karoglou and Asterios Bakolas</i>	749
7. PIGMENTS AND PAINTINGS ON MARBLE	
Painting and Sculpture Conservation in Two Gallo-Roman Temples in Picardy (France): Champlieu and Pont-Sainte-Maxence <i>Véronique Brunet-Gaston and Christophe Gaston</i>	763
The Use of Colour on Roman Marble Sarcophagi <i>Eliana Siotto</i>	773
New Evidence for Ancient Gilding and Historic Restorations on a Portrait of Antinous in the San Antonio Museum of Art <i>Jessica Powers, Mark Abbe, Michelle Bushey and Scott H. Pike</i>	783
Schists and Pigments from Ancient Swat (Khyber Pukhtunkhwa, Pakistan) <i>Francesco Mariottini, Gianluca Vignaroli, Maurizio Mariottini and Mauro Roma</i>	793
8. SPECIAL THEME SESSION: „THE USE OF MARBLE AND LIMESTONE IN THE ADRIATIC BASIN IN ANTIQUITY”	
Marble Sarcophagi of Roman Dalmatia Material – Provenance – Workmanship <i>Guntram Koch</i>	809

Funerary Monuments and Quarry Management in Middle Dalmatia <i>Nenad Cambi</i>	827
Marble Revetments of Diocletian's Palace <i>Katja Marasović and Vinka Marinković</i>	839
The Use of Limestones as Construction Materials for the Mosaics of Diocletian's Palace <i>Branko Matulić, Domagoj Mudronja and Krešimir Bosnić</i>	855
Restoration of the Peristyle of Diocletian's Palace in Split <i>Goran Nikšić</i>	863
Marble Slabs Used at the Archaeological Site of Sorna near Poreč Istria – Croatia <i>Đeni Gobić-Bravar</i>	871
Ancient Marbles from the Villa in Verige Bay, Brijuni Island, Croatia <i>Mira Pavletić and Đeni Gobić-Bravar</i>	879
Notes on Early Christian Ambos and Altars in the Light of some Fragments from the Islands of Pag and Rab <i>Mirja Jarak</i>	887
The Marbles in the Chapel of the Blessed John of Trogir in the Cathedral of St. Lawrence at Trogir <i>Đeni Gobić-Bravar and Daniela Matetić Poljak</i>	899
The Use of Limestone in the Roman Province of Dalmatia <i>Edisa Lozić and Igor Rižnar</i>	915
The Extraction and Use of Limestone in Istria in Antiquity <i>Klara Buršić-Matijašić and Robert Matijašić</i>	925
Aurisina Limestone in the Roman Age: from Karst Quarries to the Cities of the Adriatic Basin <i>Caterina Previato</i>	933
The Remains of Infrastructural Facilities of the Ancient Quarries on Zadar Islands (Croatia) <i>Mate Parica</i>	941
The Impact of Local Geomorphological and Geological Features of the Area for the Construction of the Burnum Amphitheatre <i>Miroslav Glavičić and Uroš Stepišnik</i>	951
Roman Quarry Klis Kosa near Salona <i>Ivan Alduk</i>	957
Marmore Lavdata Brattia <i>Miona Miliša and Vinka Marinković</i>	963
Quarries of the Lumbarda Archipelago <i>Ivka Lipanović and Vinka Marinković</i>	979

Island of Korčula – Importer and Exporter of Stone in Antiquity <i>Mate Parica and Igor Borzić</i>	985
Faux Marbling Motifs in Early Christian Frescoes in Central and South Dalmatia: Preliminary Report <i>Tonči Borovac, Antonija Gluhan and Nikola Radošević</i>	995
INDEX OF AUTHORS	1009

BUILDING MATERIALS AND THE ANCIENT QUARRIES AT *THAMUGADI* (EAST OF ALGERIA), CASE STUDY: SANDSTONE AND LIMESTONE

Younes Rezkallah¹ and Ramdane Marmi²

¹ École doctorale d'archéologie, Université de Paris1 Panthéon-Sorbonne, Paris, France
(younes.rezkallah@gmail.com)

² Laboratoire Géologie et Environnement, Université de Constantine 1, Constantine, Algeria
(marmi_ramdane@yahoo.fr)

Abstract

This research deals with the study of two types of building materials (sandstone and limestone) used in the Roman city of *Thamugadi* founded in 100 AD (the present Timgad), and the ancient quarries from which they had been extracted (inside a perimeter of 25 km). The field-work survey conducted in the ancient quarries of *Thamugadi* revealed sites that were previously unknown. Petrographic studies led to the identification of three sandstone lithotypes and five limestone lithotypes among the building materials sampled from fourteen monuments of the city. The survey of rock outcrops led to the identification of two main sandstone lithotypes and quarries: (T1) Djelfaoune and (T2) Mechta Rebaa. Nine limestone lithotypes and four main groups of open cast quarries or exploitation sites have been identified: Djebel Afia-Lambèse-Ain Drinn, Taouint Abderahman, Medjeba-Berbag, and Lerdham-Elghar Nithviren-Ain Cherchar.

Keywords

building materials, *Thamugadi*, quarries

Introduction

The ancient Roman colony of *Thamugadi* (*Colonia Marciana Traiana Thamugadi*)¹, the present-day Timgad, is located 35 km to the east of Batna and 21 km to the east of Lambaesis (the present Lambèse) in northeastern Algeria. It was founded in 100 AD, by the emperor Trajan and the project was conducted by the third Augustan legion (L.III.A), commanded by Lucius Manatius Gallus (GSELL 1911).

A strategic location was chosen, not so far from the Roman road that connected Lambaesis to Theveste (present-day Tébessa). Six Roman roads cross at *Thamugadi* (Fig. 1).

It was built on a small plain with an average altitude of a thousand meters (1040 m in the north and 1080 in the south). The early settlers were probably about 250 persons and the original plan was a square of 360 m sides. Quickly it became a strong and prosperous colony, which grew speedily and became a famous city. From the first half of the second century, new buildings and monuments were constructed in the eastern and western suburbs, outside of the original plan (COURTOIS 1951; LASSUS 1966).

The archaeological site and its monuments are among the most famous and attractive sites excavated in North Africa². Large studies have been devoted to them, and one can find a significant amount of literature devoted to these monuments. Unfortunately, that is not the case for the building materials. Studies of these materials are primarily focused on the building techniques and largely ignore the study of the materials themselves and their provenance (REZKALLAH 2003).

Moreover, the ancient quarries presented here and their materials remained unknown until the present work and were never studied before. These sites and other similar ones played an important role during antiquity and they should be inventoried and studied in order to take their own place in the archaeological atlas of Algeria (REZKALLAH 2017).

Geological view

Timgad is situated in the center of the sedimentary basin that bears the same name. In the geological series, the basin essentially belongs to the Cretaceous and the Neogene (Miocene and Pliocene); however, gypsiferous Triassic formations can be observed in some abnormal positions (MARMI 1995).

The rocks of the Cretaceous (Upper Cretaceous) are represented essentially by limestone and marls but

1 CIL.VIII.17842-43= ILS 6841.

2 The first excavations date back to 1880 and continued till 1955. The excavations results were regularly published, particularly in BCTH (Bulletin du Comité de Travaux Historiques et Scientifiques).




Fig. 1. The location of the ancient quarries of Timgad (ancient Thamugadi)




Fig. 2. Geological series in the Basin of Timgad



Fig. 3. The monuments concerned in the sampling and study of and building materials



Fig. 4. The Djelfaoune quarries and sandstone lithotype.

A - The Djelfaoune Sandstone quarries;

B1 - Photomicrograph of the T1 sandstone lithotype: subrounded and heterogeneous quartz (PPL, X4);

B2 - Iron oxides in T1 lithotype (NPL, x4)



Fig. 5. The Mechta Rebaa quarries and sandstone lithotype.

A - General view of the northern part of Mechta Rebaa quarries;

B1 - Photomicrograph of homogeneous quartz in the T2 lithotype sandstone samples (PPL, x2);

B2 - Photomicrograph of the T2 lithotype sandstone with grains of glauconite (NPL, x4)

those of the Miocene are formed of clays and sandstones.

The brittle tectonics (faults, fractures, cracks) induced discontinuities in limestone and sandstone rocks, facilitating the exploitation and extraction of stone materials.

The two main building materials discussed in this paper are abundant near Thamugadi: sandstone in the immediate vicinity of the site and limestone located a few kilometers around the city (Fig. 2).

Archaeological monuments

Due to the large amount of monuments known at Thamugadi, only a few of them have been chosen for this project. Thus, fourteen monuments were selected for the current research (Fig. 3). Then, a selective sampling of sandstone and limestone building materials was done in each monument.



Fig. 6.
 General view of the limestone quarries, extraction sites and outcrops around Thamugadi.
 A: Djebel Afia quarries;
 B: Ain Drinn outcrops and exploitations;
 C: Lambese exploitations;
 D: Opencast quarries of Taouint Abderahmane;
 E: Eastern extraction site in Taouint Abderahmane (red marmoreal sandstone);
 F: Medjeba opencast quarries;
 G: Berbaga outcrops;
 H: Ain Cherchar outcrops;
 I: North-western part of Lardham opencast quarries;
 J: Elghar Nithviren limestone quarries (Site 2)

The present study concerns the following monuments: a part of the northeastern primitive wall of the colony, the Capitol, the Theatre, the southern great baths, the library, the Curia, the eastern small baths which occupy insula no. 79, tinsula 01, insula 11, insula 12, insula 72, the *Cardo maximus*, the *Decumanus maximus* and the forum. The three last sites have provided three different limestone samples of pavement slabs. This concerns the bluish gray limestone of the Forum, bluish limestone including fossils of the two main streets *intra-muros* (*Cardo* and *Decumanus maximus*), and the red marmoreal limestone collected from the scattered pavement in the courtyard of the Capitol. All these monuments date from between the 2nd and 5th century.

Quarries and extraction sites

In order to identify the ancient quarries and extraction areas near Timgad, we conducted an archaeological survey on the outcrops of sandstone and limestone, using a 25 km perimeter around the ancient city (Fig. 1).

The mapping of the ancient quarries in the region was carried out systematically at the same time as the outcrops were surveyed. A limited budget and time constraints led to the use of a simple GPS (Garmin e-trex version) for mapping quarries, extractions, and sampling sites. Currently, a total of fourteen sites have been identified, and further surveys will probably extend this number. With regard to site selection, there are two




Fig. 7. Photomicrographs of thin sections of building materials from Thamugadi: A: Bioclastic limestone C1, full of bryozoans and echinoderms (PPL, x2); B: Fossil-rich limestone C2 with rounded elements (NPL, x2); C: Elongated and rounded elements, and calcite spots in the C3 limestone lithotype (NPL, x2); D: Dolomitic microcrystalline limestone C4, with isometric crystals (NPL, x2); E: The marmorale blue limestone C5, with rhombohedral crystals (NPL, x2); F: Sandstone lithotype G1, with heterogeneous quartz (PPL, x2); G: Sandstone lithotype G2, with homogeneous quartz (NPL, x2); H: Laminated sedimentary structures, alternating fine and relatively coarse grains of quartz in the G3 lithotype (NPL, x2)

issues worth mentioning here: 1) unfortunately, some areas remains inaccessible and dangerous; 2) the second, is that the assistance of the local population and some shepherds were of great help to us, as they - more than anyone else- know the outcrops surrounding the ancient city extremely well.

Two main sandstone quarries were identified: Djelfaoune, 2 km in the direction of the south-west and Mechta Rebbaa, 7 km to the north-east. One small extraction site was also discovered near the Byzantine citadel. The microscopic examination conducted on the samples showed that the rocks are identical as those at Djelfaoune. As the sites are near to each other we prefer to associate them with the same quarries (Djelfaoune) (Fig. 4A).

The common element to these sites is that the sandstone consists of laminated layers or strata that are separated by thin stratification joints. The average thickness of beds in the Djelfaoune quarries is about 60 cm,

while the range of thickness in Mechta Rebbaa varies from 30 to 60 cm. This natural stratification allows the rock beds to cleave horizontally and offers cutting facilities to the stone cutters. The inclination of the sandstones bed rocks in Mechta Rebbaa probably offered supplementary facilities (Fig. 5A).

The survey of limestone outcrops allowed the identification of four main groups of open cast quarries and exploitation sites, located a few kilometers around the ancient city (Fig. 6).

The first is the Lambèse group, located 21 km to the west of Thamugadi, and it is represented by two separate sites: the quarries located at the top of Djebel Afia (Fig. 6A), with metric beds, dated to the Upper Cenomanian; the ancient exploitations of Ain Drinn (Fig. 6B) and Haute Lambèse (Fig. 6C), belonging to the Middle-Upper Turonian, located 2.5 km south-west of the Roman military camp of Lambaesis.

The second group is located 23 km to the North of Timgad, and includes the quarries of Taouint Abderahman (Fig. 6D) and extraction sites of the same locality (Fig. 6E). Opened in the Marly limestone outcrops belonging to the Upper Cenomanian, this is also characterized by metric beds.

The third is situated 7-10 km south of the city, and includes the Medjeba opencast quarries (Fig. 6F) and Berbagha outcrops (Fig. 6G). These strata are not indicated on the geological map of Tazoult, since that is a small-scale map on which it is difficult to register all the small details. These are probably of Upper Coniacian age.

The fourth group concerns the open cast quarries of Lerdham (Fig. 6I) and Elghar Nithviren (Fig. 6J), in addition to the outcrop of Ain Cherchar (Fig. 6H). According to the geological map of Tazoult, it appears that this group belongs also to the Cretaceous, and is identified as crystalline massif limestone aged to the Upper Maestrichtian (VILA 1977).

In most cases here, the limestone beds are crossed by vertical and horizontal cracks, giving a lot of facilities for extracting blocks, particularly in the Lardham open cast quarries, where the natural polygonal blocks only need to be dressed to be ready for use (Fig. 6I).

Macroscopy and petrography

The different types of samples of building stone samples were inspected with the aid of a magnifying glass on fresh breaks. This method allows 5 to 15 times magnification, which helps in the identification of some textural details, the selection and making a primary typology classification of samples (COUTELAS 2003).

The thin sections prepared from these samples were analyzed systematically under a polarizing microscope. The thin sections of the samples collected in the monuments of Thamugadi were compared with those prepared from the stone samples that come from the ancient quarries. This method was already applied by other scholars to the study of ancient stones and tesserae (BUGINI, FOLLI 2009; LAPUENTE, TURI *et al.* 2009)

Results and discussion

The mineralogical approach through the petrography of the thin sections prepared from the building materials sampled in the monuments of Thamugadi led to the identification of three sandstone lithotypes (G1-3) (Fig. 7F-G) and five limestone lithotypes (C1-5) (Fig. 7A-E). These lithotypes are discussed in more detail here. The samples collected in the ancient quarries and outcrops allowed the identification of two sandstone lithotypes (T1) for Djelfaoune (Fig. 4B1-B2), and (T2) for Mechta Rebaa (Fig 5B1-B2), each lithotype being paired

with the appropriate one identified in the building materials of Thamugadi. The nine limestone lithotypes (Q1-Q9) that were identified in the quarries and outcrops are summarized at the end of this paper (Fig. 8).

Lithotype G1, named light yellowish sandstone on the basis of visual examination, shows a joined middle to coarse grain size quartz under the microscope. The grains are heterogeneous but generally subrounded, although unusual angular grains were also observed. The presence of some glauconite grains and traces of iron oxides were also detected (Fig. 7F). This lithotype is represented essentially by the dressed stone used in the squared-stone masonry of the Capitol and the Theatre. We observe it also in the vertical facing dressed stones and rubble stones of walls in *opus africanum* of the southern great baths, library, eastern small baths, insula 72, Theatre and Capitol. The petrographic comparisons of the samples collected in the Citadel extraction site and Djelfaoune quarries, show a great resemblance in their structure and mineralogical composition with this lithotype. There is no doubt that G1 sandstone, which constitutes the stone most used as building material in the studied monuments, was extracted from the further quarries, situated near the site. Indeed, this lithotype corresponds perfectly to the first sandstone lithotype T1, identified in the samples collected from the Djelfaoune and Citadel extraction site, as both have the same structure and compounds (Fig. 4B1-B2). As in G1, the grains are also subrounded and heterogeneous, with iron oxides traces and glauconite.

Lithotype G2, or the dark yellowish sandstone, is slightly different in its color from G1, but it is difficult to differentiate them. However, petrographic examination shows homogeneous grains of quartz and scattered glauconite. The elements are fine grain size and subrounded to rounded (Fig. 7G). Iron oxides are present as traces as in G1. The G2 lithotype is found in the vertical slab stones used for the separation between the upper and lower stands of the theatre, and in the building of some external parts of walls in *opus mixtum* in the insulae 11 and 12. The samples of squared rubble used in the construction of the primitive wall of the colony also show the same material. As in the case with lithotypes G1 and T1, the concordance between G2 and T2 recognized in the samples of Mechta Rebaa quarries is clear (Fig. 5). The T2 lithotype shows the same size and subrounded to rounded homogeneous quartz, with scattered glauconite and iron oxide traces (Fig. 5B1-B2).

Geologically, the inclination of the strata on the outcrops is an advantage for extracting great slabs, and probably such detail would not have been ignored by Roman architects (Fig. 5A).

The third lithotype, G3, is a brown sandstone, characterized by laminated sedimentary structures,










Simplified Name	Origin & Map Location	Litho-type	Microscopic definition	Geological age	Identification in building materials	photomicrograph
Bluish hard Limestone	Djebel Afa Quarries (n°1)	Q1	Micritic Limestone with calcite recrystallization filling the microcracks	Upper Cenomanian	No	
Gray Limestone with Fossils	Ain Drinn and Lambèse Exploitations (n°2 and 3)	Q2	Bioclastic Limestone with Annelids	Middle-Upper Turonian	No	
Marmoreal Red Limestone	Taouint Abderahmane Quarries (n°4)	Q3	Microconglomerate Limestone with ferruginous facies	Superior Cenomanian	No	
Bluish Gray Limestone of Taouint A.	Taouint Abderahmane Quarries (n°4)	Q4	Bioclastic Limestone with spherical elements	Superior Cenomanian	No	
Bluish Gray Limestone of Medjeba	Medjeba Quarries (n°5)	Q5	Bioclastic Limestone with Biseriates	Upper Cenomanian	No	
Bluish Gray Limestone Of Berbaga	Berbaga Outcrops (n°6)	Q6	Bioclastic Limestone with Bryozoans	Upper Cenomanian	lithotype C1 (Pavement Slabs Cardio & Decumanus Maximus)	
Whitish Beige Limestone of Ain Cherchar	Ain Cherchar Outcrops (n°7)	Q7	Bioclastic Limestone with Large Debris of Lamellibranches	Upper Maastrichtian	No	
Bluish Gray Limestone of Aghrout Lerdham	Lerdham Quarries (n°8)	Q8	Bioclastic Limestone Rich with Fossils and more or less Rounded Elements	Upper Maastrichtian	Lithotype C2 (Pavement Slabs from Forum)	
Whitish Beige Limestone of Elghar Nithviren	Elghar Nithviren Quarries (n°9)	Q9	Biclastic Limestone with Calcite Ranges	Upper Maastrichtian	Lithotype C3 (rubble stones from Insulae 12 & 72, Library and Capitol)	

Fig. 8. Limestone lithotypes from the quarries of Timgad region: summarized results

alternating fine and relatively coarse grains of quartz (Fig. 7H). The iron oxides are more important than in the two previous types, explaining the brown color of this stone.

This type of stone is attested in some blocks used in insula 01, Curia and foundations of the external wall of the Capitol. Unfortunately, no extraction site for the G3 lithotype can be proposed as no matching lithotypes were found.

Five limestone lithotypes (C1-5) were identified among the samples of building materials collected in Thamugadi.

The first one, C1, is the bluish limestone including fossils (Fig. 7A). It is a bioclastic limestone, full of bryozoans, echinoderms, gastropods, sea urchin spines and lot of rolled oolitic elements. It was used as pavement slabs for the two main streets (Cardo maximus and Decumanus maximus) and as rubble stones for the small masonry in the library. These bioclasts are comparable to those observed in the bioclastic limestone sample of Berbaga Q6, but the rounded elements are not comparable (Fig. 8). This means that no final conclusion can be drawn based on the current data. Further thorough surveys in these outcrops and, if possible, in the northern upstream of Djebel Bouarif, could lead to a positive conclusion about the origin of this lithotype.

The second lithotype, C2, is a bluish gray limestone. It is also a bioclastic stone, and - like C1 - is rich with fossils, but the other elements here are more or less rounded than in C1 (Fig. 7B). The samples of this type come either from the pavement slabs of the Forum, or from some rubble stones of the southern great baths and insula 72. This lithotype shows similarities with the fossil contents of lithotype Q8, belonging to Aghrout Lerdham open cast quarries (Fig. 8). Based on these results, we think that Aghrout Lerdham produced the stone slabs used for paving the Forum.

The third lithotype C3, is a whitish beige colored bioclastic limestone. It is represented essentially by rubble stones sampled from the external wall of the Capitol, from small masonry walls in insulae 12 and 72, the library, and in the eastern small baths. These rubble-stones are fragmentary parts of architectonic elements, such as capitals or columns, reused here for building purpose. Under the microscope, this type is characterized by elongated and rounded elements, and calcite spots (Fig. 7C). The comparison of this type with the thin sections of stones collected in the ancient quarries and limestone outcrops, shows that it looks like the bioclastic limestones of Elghar Nithviren Q9 (Fig. 8).

The C4 lithotype was identified in samples of the red marmoreal limestone, which was used as pavement slabs in the courtyard of the Capitol. The microscopic examination shows a dolomitic microcrystalline limestone,

with automorphic and isometric crystals. It contains microfissures filled out with calcite and iron oxides. No fauna or bioclastic elements can be observed here (Fig. 7D).

The marmoreal blue limestone sampled from fragments of columns, reused as small blocks in the Capitol, offers another lithotype C5, which is a bioclastic limestone including very coarse elongated shell debris. Impregnated with few iron oxides and contains rhombohedral crystals, it is probably a dolomite (Fig. 7E).

Unfortunately none of the nine lithotypes found in the ancient quarries and limestone outcrops correspond to these two last types.

Conclusion

The sampling done in the selected monuments of Thamugadi did not provide definitive results about all the different varieties of stones used for building in this Roman colony. However, it did allow for the identification of the two main stone varieties used either for building or paving. The sandstone was frequently used as building material (dressed stones, slabs, blocks and rubble) and as pavements of secondary street, while the limestone was widely used for paving the two main streets, also the Forum, and in rare case as rubble.

The historians and archaeologists think that the choice of this site for a colony was dictated by military considerations, such as the strategic features of the site and the abundance of water resources. Considering the important use of the sandstone in the buildings, the abundance of those materials extracted in nearby quarries and the extraction facilities offered by the outcrops, we conclude that the geology also influenced that choice.

The fieldwork surveying conducted in the ancient quarries of Thamugadi revealed sites that were previously unknown. The petrographic and laboratory studies led to the identification of the Djelfaoune and Mechta Rebaa sandstone quarries that provided the city with two different varieties of rocks.

Among the ancient limestone quarries identified, only Aghrout Lerdham and Elghar Nithviren seem to have furnished limestones to the city. As the identified building materials that belong to Elghar Nithviren lithotype are represented by reused fragments of architectonic elements, we think that this quarry was exploited for this reason (architectonic elements). The limestone variety of the Berbaga outcrops shows some similarities with the bluish limestone used for the pavement slabs of the Cardo and Decumanus maximus.

Further geochemical investigations (chemical analysis, stable isotopes, etc) and mineralogical ones (XRD) will complete the present study and bring new elements for the ancient stones database of the region.

ACKNOWLEDGEMENTS

The authors are grateful to Prof. F. Villeneuve (Université de Paris1), Dr. P-M. Blanc (Université de Paris1, UMR 7041 ARSCAN), Dr. F. Djaiz (Université de Batna), M. Belkares (Conservator of Thamugadi) and H. Oukaour (EPHE) for their valuable help. Special thanks go to S. Pachulski from ESRI France for his generous help and ArcGis facilities and assistance.

They also want to thank le Laboratoire de Microscopie USR 3225 SIMO (MAE) for allowing the use of their equipment. Special gratitude goes to numerous persons and shepherds for their help, particularly Ammi Houcine Benguouga.

BIBLIOGRAPHY

- BUGINI R., FOLLI L. 2009: "On tesserae of roman mosaics in Lomardy (Italy)", in *ASMOSIA VII*, 547-559.
- COURTOIS C. 1951: *Timgad antique Thamugadi*. Service des Antiquités, Alger.
- COUDELAS A. 2003: *Pétoarchéologie du mortier de chaux gallo-romain essai de reconstitution et d'interprétation des chaînes opératoires; du matériau au métier antique*. Université de Paris1, Paris, 2003. Unpublished Phd Thesis in archaeology.
- GSELL S. 1911: *Atlas archéologique de l'Algérie*. Alger.
- LAPUENTE P., TURI B., BLANC Ph. 2009: "Marbles and coloured stones from the theatre of Caesaraugusta (Hispania); preliminary study", in *ASMOSIA VII*, 309-322.
- LASSUS J. 1966: "Une opération immobilière à Timgad", *Mélanges d'archéologie et d'histoire n°3*, Paris, 1221-1231.
- MARMI R. 1995: *Les Sebkhas du Sud-Constantinois et leur cadre géologique apports sédimentologiques et géochimiques*, Université de Nancy 1, Nancy, 1995. Unpublished Phd Thesis in geology.
- REZKALLAH Y. 2003: *Architectural and Technical study of typical types of the Roman Dwellings at Thamugadi*, University of Baghdad, 2003. Unpublished. Master thesis in archaeology.
- REZKALLAH Y. 2017: "ArcDZGIS, un SIG au service de l'Atlas archéologique de l'Algérie", *Libyca 36 (Actes du colloque international "La Numidie, Massinissa et l'Histoire")*, 271-283.
- VILA J. M. 1977: *Notice explicative de la carte géologique au 1/50.000; feuille (201) Tazoult*, Ministère de l'industrie, des mines et de l'énergie, Service de la carte géologique de l'Algérie, Alger, 1977.